



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 13579 Lot No.: 0019 Date: 01/19/2010

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2580	1/4" EHS GS	6650	7780	116.9	STRAND FAILED
			7840	117.8	STRAND FAILED
			7890	118.6	STRAND FAILED
AVERAGE			7836	117.7	

Regards,

Javier Alegria
Quality Management System Head

ma