



# PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 14148      Lot No.: 0165      Date: 06/25/2010

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2582	5/16" EHS GS	11200	12790	114.1	STRAND FAILED
			12670	113.1	STRAND FAILED
			12680	113.2	STRAND FAILED
AVERAGE			12713	113.4	

Regards,

Javier Alegria  
Quality Management System Head

ma