



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

June 28, 2007

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 257379-1 Lot No.: 257379-1 Date: 6/27/07

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-1587	5/8" EHS	42,400	46,260	108.9	Strand failed midspan
			46,440	109.5	Strand failed midspan
AVERAGE			46,350	109.2	

Regards,

Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

File 31