



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

January 11, 2010

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 262266 Lot No.: 262266 Date: 1/4/10

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-1587	5/8" EHS	42,400	50,000	117.9	No strand failure.
			50,000	117.9	No strand failure.
AVERAGE			50,000	117.9	

Regards,

Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

File 94