



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

May 30, 2007

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 58161 Lot No.: 58161 Date: 5/16/07

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2580	1/4" EHS GS	6,650	7470	110	Strand failed
			7470	110	Strand failed
AVERAGE			7470	110	

Regards,

Scott L. Sanderson
Corporate Quality Assurance Engineer

ma