



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 8357 Lot No.: 6030 Date: 02/15/2007

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2584	7/16" EHS GS	20800	25290	121.6	STRAND FAILED
			25330	121.8	STRAND FAILED
			25480	122.5	STRAND FAILED
AVERAGE			25366.7	122.0	

Regards,

Javier Alegria
Quality Management System Head

ma