



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 9020 Lot No.: 6236 Date: 02/14/2007

| BRACE-GRIP® DE CAT NO. | STRAND SIZE (in.) | STRAND MBS (lbs.) | MAXIMUM LOAD (lbs.) | % MBS | FAILURE MODE AT MAX. LOAD |
|---------------------------|----------------------|-------------------------|---------------------------|----------|------------------------------|
| BRG-2583 | 3/8" EHS GS | 15400 | 17600 | 114.3 | STRAND FAILED |
| | | | 17690 | 114.9 | STRAND FAILED |
| | | | 17660 | 114.7 | STRAND FAILED |
| AVERAGE | | | 17650 | 114.6 | |

Regards,

Javier Alegria
Quality Management System Head

ma