



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 9492 Lot No.: 6305 Date: 02/15/2007

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2585	1/2" EHS GS	26900	31620	117.5	STRAND FAILED
			31800	118.2	STRAND FAILED
			31850	118.4	STRAND FAILED
AVERAGE			31756.7	118.0	

Regards,

Javier Alegria
Quality Management System Head

ma