



# PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

February 25, 2008

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2583	3/8" EHS G.S.	15,400	16,450	107	Strand broke mid-span at maximum load
			16,400	107	Strand broke mid-span at maximum load
AVERAGE			16,425	107	

Regards,

**Scott L. Sanderson**  
Corporate Quality Assurance Engineer

ma

cc: File 31  
S. Wilburn