



# PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 9854      Lot No.: 7038      Date: 02/15/2007

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2583	3/8" EHS GS	15400	17450	113.3	STRAND FAILED
			17510	113.7	STRAND FAILED
			17380	112.9	STRAND FAILED
AVERAGE			17446.7	113.3	

Regards,

Javier Alegria  
Quality Management System Head

ma