



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 10170 Lot No.: 7162 Date: 06/15/2007

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2584	7/16" EHS GS	20800	25580	122.9	STRAND FAILED
			25380	122.0	STRAND FAILED
			25360	121.9	STRAND FAILED
AVERAGE			25440	122.3	

Regards,

Javier Alegria
Quality Management System Head

ma