



# PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 10169      Lot No.: 7171      Date: 06/27/2007

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2583	3/8" EHS GS	15400	17780	115.4	STRAND FAILED
			17620	114.4	STRAND FAILED
			17920	116.3	STRAND FAILED
AVERAGE			17773	115.3	

Regards,

Javier Alegria  
Quality Management System Head

ma