



# PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 10008 Lot No.: 7178 Date: 06/27/2007

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2582	5/16" EHS GS	11200	12900	115.1	STRAND FAILED
			12990	115.9	STRAND FAILED
			12970	115.8	STRAND FAILED
AVERAGE			12953	115.6	

Regards,

Javier Alegria  
Quality Management System Head

ma