



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 10364 Lot No.: 7274 Date: 10/31/07

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2580	1/4" EHS GS	6650	8030	120.7	STRAND FAILED
			7980	120.0	STRAND FAILED
			7990	120.1	STRAND FAILED
AVERAGE			8000	120.2	

Regards,

Javier Alegria
Quality Management System Head

ma