



# PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 10366 Lot No.: 7276 Date: 10/31/2007

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2583	3/8" EHS GS	15400	17100	111.0	STRAND FAILED
			17120	111.1	STRAND FAILED
			17100	111.0	STRAND FAILED
AVERAGE			17106	111.0	

Regards,

Javier Alegria  
Quality Management System Head

ma