


April 13, 2010

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2585	1/2" EHS G.S.	26,900	30,307	112.67	Strand broke between DEs at max. load.
			30,348	112.82	Strand broke between DEs at max. load.
AVERAGE			30,328	112.75	

Regards,



Scott L. Sanderson  
**Corporate Quality Assurance Engineer**

ma

cc: File 94  
 J. Reilly