



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

April 13, 2010

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.:	284861	Lot No.:	284861	Date:	4/8/10
BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2580	1/4" EHS G.S.	6,650	7,547	113.49	Strand failed at max. load.
			7,552	113.56	Strand failed at max. load.
AVERAGE			7,550	113.53	

Work Order No.:	84935	Lot No.:	84935	Date:	4/8/10
BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2585	1/2" EHS G.S.	26,900	30,799	114.49	Strand failed at max. load.
			30,870	114.76	Strand failed at max. load.
AVERAGE			30,835	114.63	

Regards,

Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly