



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 12872 Lot No.: 9196 Date: 07/15/2009

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2582	5/16" EHS GS	11200	12990	115.9	STRAND FAILED
			12930	115.4	STRAND FAILED
			12860	114.8	STRAND FAILED
AVERAGE			12926	115.3	

Regards,

Javier Alegria
Quality Management System Head

ma