



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 13400 Lot No.: 9344 Date: 12/10/2009

| BRACE-GRIP® DE CAT NO. | STRAND SIZE (in.) | STRAND MBS (lbs.) | MAXIMUM LOAD (lbs.) | % MBS | FAILURE MODE AT MAX. LOAD |
|---------------------------|----------------------|-------------------------|---------------------------|----------|------------------------------|
| BRG-2580 | 1/4" EHS GS | 6650 | 7810 | 117.4 | STRAND FAILED |
| | | | 7860 | 118.1 | STRAND FAILED |
| | | | 7800 | 117.2 | STRAND FAILED |
| AVERAGE | | | 7823 | 117.5 | |

Regards,

Javier Alegria
Quality Management System Head

ma