



# PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

July 24, 2007

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 9492      Lot No.: 6293      Date: 10/31/06

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2585	1/2" EHS G.S.	26,900	33,380	124.1	Strand failed
			33,290	123.7	Strand failed
			33,150	123.2	One wire of grip failed.
AVERAGE			33,273	123.7	

Regards,

Javier Alegría  
Quality Management System Head

ma

File 31