



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 16616 Lot No.: 1188 Date: 07/07/2011

| BRACE-GRIP® DE CAT NO. | STRAND SIZE (in.) | STRAND MBS (lbs.) | MAXIMUM LOAD (lbs.) | % MBS | FAILURE MODE AT MAX. LOAD |
|---------------------------|----------------------|-------------------------|---------------------------|----------|------------------------------|
| BRG-2582 | 5/16" EHS GS | 11200 | 12760 | 113.9 | STRAND FAILED |
| | | | 12670 | 113.1 | STRAND FAILED |
| | | | 12790 | 114.1 | STRAND FAILED |
| AVERAGE | | | 12740 | 113.7 | |

Regards,

Javier Alegria
Quality Management System Head

ma