



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 15214 Lot No.: 0322 Date: 11/22/2010

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2582	5/16" EHS GS	11200	12700	113.3	STRAND FAILED
			12720	113.5	STRAND FAILED
			12670	113.1	STRAND FAILED
AVERAGE			12696	113.3	

Regards,

Javier Alegria
Quality Management System Head

ma

File 94

cc: J. Reilly