



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 15798 Lot No.: 1041 Date: 02/10/2011

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2585	1/2" EHS GS	26900	30320	112.7	STRAND FAILED
			30410	113.0	STRAND FAILED
			30240	112.4	STRAND FAILED
AVERAGE			30323	112.7	

Regards,

Javier Alegria
Quality Management System Head

ma