



June 8, 2023

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Lot No.: 599897

Date: 6/5/23

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2582	5/16" EHS G.S.	11,200	12,841	115	One wire on one dead end broke at max load. No strand failure occurred.
			13,143	117	One wire on one dead end broke at max load. No strand failure occurred.
		AVERAGE	12,992	116	

Regards,

A handwritten signature in black ink that reads "Scott Sanderson". The signature is written in a cursive, flowing style.

Scott L. Sanderson

Senior Quality Engineer

RMB

cc: File 94, M. Miller

PLP.COM