

July 21, 2023

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Lot No.: 597785 Date: 7/14/23

| BRACE-GRIP®<br>Dead-End CAT.<br>NO. | Strand<br>Size (in.) | Strand<br>RBS (lbs.) | Maximum<br>Load (lbs.) | % of<br>RBS | Failure Mode at Maximum<br>Load                             |
|-------------------------------------|----------------------|----------------------|------------------------|-------------|---|
| BRG-2582                            | 5/16"                | 11,200               | 13,865                 | 124         | Strand broke mid span. No slip from either deadend.         |
|                                     | EHS<br>G.S.          |                      | 13,707                 | 122         | Strand broke mid span.<br>No slip from either dead-<br>end. |
|                                     |                      | AVERAGE              | 13,786                 | 123         |   |

Regards,

Scott L. Sanderson

Senior Quality Engineer

RMB

cc: File 94, M. Miller